

Daily Skin Hydrator

B-2006B-02

DESCRIPTION

This skin cream contains 1% **RHEOLUXE® 812**, which increases the shear thinning viscosity and can be compared to B-2006A-02, B-2006C-02, B-2006D-02, B-2006E-02 and B-2006J-02.

SPECIFICATIONS

Viscosity: RV, Spindle 7. 5rpm
84,800 cps

pH: 5.0-6.0

Appearance: Thick white cream

Phase	Ingredient	Supplier	%w/w
A	Deionized Water		74.50
	Glycerin		3.00
B	Mineral Oil		5.00
	Caprylic/Capric Triglyceride (Palmeester 3595)	KLK Oleo	5.00
	Dimethicone (KF-96L-2s)	Shin Etsu	3.00
	Cetareth-20 (Cremophor A 20)	BASF	3.00
	Cetyl Alcohol (Tego Alkanol 16)	Evonik	2.00
	Cetearyl Alcohol (Tego Alkanol 1618)	Evonik	2.00
	Caprylhydroxamic Acid (and) Caprylyl Glycol (and) Glycerin (Spectrastat)	Inolex	1.00
	Stearic Acid		0.50
C	Bis-Lauryl Cocaminopropylamine/HDI/PEG-100 Copolymer (RHEOLUXE® 812)	Elementis	1.00
D	Citric Acid		q.s

Procedure:

1. Heat Phase A and Phase B separately to 75°C.
2. Add Phase B to Phase A with moderate speed mixing.
3. Transfer to a propeller mixer and cool to room temperature.
4. Add Phase C and mix for 10 minutes.
5. Add Phase D with mixing as necessary.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Registered trademark of Elementis Specialties, Inc.

V02 March 2018

North America

Elementis
469 Old Trenton Road
East Windsor, NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563