

## BENTONE HYDROCLAY™ 2000

### Non-animal Origin Rheological Additive For Aqueous Cosmetics And Toiletries

#### GENERAL INFORMATION

**BENTONE HYDROCLAY™ 2000** additive is a highly beneficiated, easily dispersible powdered smectite clay. It imparts thixotropic viscosity and good suspension control to the water phase of cosmetics.

#### INCI NAME

Hectorite

#### CHEMICAL & PHYSICAL PROPERTIES

% Drying Loss When Packed	max. 7.5
% Thru 200 Mesh Sieve	94.0 – 100.0
Gel Ability (cP)	1600 - 2400

These are typical properties not to be used for specification purposes

#### APPLICATIONS

- Oil in Water Emulsions
- Water in Oil Emulsions
- Creams
- Lotions
- Anti-Perspirants
- Deodorants
- Colour Cosmetics
- Face Packs
- Facial Make-Up
- Sun Care Products
- Hair Care Products

#### KEY PROPERTIES

- Vegan
- Is easily processed as a powder or pre-gel
- Increases the viscosity of the aqueous phase and stabilises viscosity on ageing, at varying temperatures and under different shear conditions
- Imparts thermostable thixotropy/pseudoplasticity
- Provides excellent suspension control

- Reduces phase separation and syneresis
- Is non-abrasive and imparts smooth silky feel to cosmetics and personal care products

#### INCORPORATION

**BENTONE HYDROCLAY™ 2000** additive is easy to process. No chemical activator or increased temperature is required.

- Add **BENTONE HYDROCLAY™ 2000** to a vessel containing only water. If necessary, adjust pH level to less than pH 7.5. High pH may lead to dispersion difficulties due to rapid hydration of **BENTONE HYDROCLAY™ 2000**, whereas a low pH leads to reduced efficiency and excessively long hydration times.
- Mix at highest practicable speed for 10 minutes.
- After sufficient hydration time, introduce glycols, defoamers, biocides, dispersants etc. (mix).
- Add pigments, fillers, active ingredients and disperse.
- Complete dilution.

#### LEVELS OF USE

Typical use levels of **BENTONE HYDROCLAY™ 2000** are 0.3% to 1.0% based on total system weight.

#### HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

#### STORAGE RECOMMENDATIONS

Store in a dry place. **BENTONE HYDROCLAY™ 2000** additive will absorb atmospheric moisture in high humidity conditions.

#### SHELF LIFE

**BENTONE HYDROCLAY™ 2000** has a minimum shelf life of 4 (four) years from date of manufacture.

*continued...*

## BENTONE HYDROCLAY™ 2000

### QUALITY ASSURANCE

Quality and continuous improvement are paramount to our business. Facility manufacturing Bentone Hydroclays™ has established strong integrated management system and holds ISO 9001, ISO 14001, and ISO 45001 certifications.

### SUSTAINABILITY

**BENTONE HYDROCLAY™ 2000** is a raw material approved by Ecocert Greenlife in accordance with the COSMOS Standard.



**COSMOS  
APPROVED**

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

© Copyright 2020, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

™ Trademark of Elementis Specialties, Inc.

August 2020

#### North America

Elementis  
469 Old Trenton Road  
East Windsor, NJ 08512, USA  
Tel.: +1 609 443 2500  
Fax: +1 609 443 2422

#### Europe

Elementis UK Ltd.  
c/o Elementis GmbH  
Stolberger Strasse 370  
50933 Cologne, Germany  
Tel.: +49 221 2923 2066  
Fax: +49 221 2923 2011

#### Asia

Deuchem (Shanghai) Chemical Co., Ltd.  
99, Lianyang Road  
Songjiang Industrial Zone  
Shanghai, China 201613  
Tel.: +86 21 5774 0348  
Fax: +86 21 5774 3563